

We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

4,800

Open access books available

122,000

International authors and editors

135M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities



WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com



Development of Flexible Cu(In,Ga)Se₂ Thin Film Solar Cell by Lift-Off Process

Yasuhiro Abe, Takashi Minemoto and Hideyuki Takakura
Ritsumeikan University
Japan

1. Introduction

Clean energy resources as an alternative to fossil fuels has been required. Photovoltaics is the most promising among renewable energy technologies. On the other hand, the cost of the electrical energy generated by the solar cells was higher than that generated by fossil fuels. The cost reduction of the solar cell is therefore required.

Since high-conversion efficiencies have been demonstrated for solar cells using GaAs substrates in 1977 (Kamath et al., 1977; Woodall et al., 1977), a critical problem is how to reduce power generation cost. The characters required to solar cells strongly depend on its applications. In particular, thin film solar cells are promising for terrestrial applications, because thin film solar cells are more advantageous than bulk type solar cells in terms of consumption of raw materials. Konagai et al. fabricated the thin film solar cells on a single crystalline GaAs substrate by the liquid phase epitaxy method, and focused on the reuse of GaAs substrates by detaching these thin film solar cells from the GaAs substrates (Konagai et al., 1978). Konagai et al. named this separation technique the Peeled Film Technology (PFT). This is the invention of the lift-off method in solar cell development. A specific explanation of the PFT is as follows. An Al_{1-x}Ga_xAs layer was introduced between the thin film solar cell and the GaAs substrate as a release layer. The thin film solar cell was separated from the GaAs substrate by etching the Al_{1-x}Ga_xAs layer by the HF solution, because Al_{1-x}Ga_xAs was readily dissolved by the HF solution compared to GaAs. Since a chemical technique was mainly used for the peeling, this method is defined as a chemical lift-off process. Recently, this has been researched as the epitaxial lift-off (ELO) method (Geelen et al., 1997; Schemer et al., 2000, 2005a; Voncken et al., 2002; Yablonovitch et al., 1987).

On the other hand, the cleavage of lateral epitaxial films for transfer (CLEFT) process, where the thin film was mechanically peeled, was developed as a transfer method of a single crystalline GaAs thin film (McClelland et al., 1980). A specific explanation of the CLEFT process is as follows. A photoresist was applied to a surface of a GaAs substrate. The photoresist was patterned with equally-spaced stripe openings by standard photolithographic techniques. Next, a GaAs layer was grown on this patterned substrate surface. In this case, a GaAs layer was grown on only the openings of the photoresist. The lateral growth of a GaAs layer occurs during the GaAs deposition. A single crystalline GaAs layer is therefore formed on the photoresist. Alternative substrate was bonded onto this

surface with epoxy glue. The single crystalline thin film was transferred to the alternative substrate by applying tensile strain. The CLEFT process is therefore defined as a mechanical lift-off process.

Unfortunately, the conversion efficiency of the GaAs thin film solar cell using the lift-off process was lower than that of the GaAs bulk solar cell (Schermer et al., 2006). Recently, comparable conversion efficiencies have been demonstrated (Bauhuis et al., 2009).

On the other hand, the energy:weight ratio of the photovoltaic module is a very important index for space applications. Integration of high-efficiency III-V solar cells with light weight substrates is required. Schermer et al. developed high-efficiency III-V solar cells with light-weight by the ELO process using the GaAs substrate (Schermer et al., 2005b).

In addition, the lift-off process was applied to reuse Si substrates (Bergmann et al., 2002; Brendel, 2001). Moreover, the lift-off process was applied to fabricate flexible solar cells in the developments of II-VI and I-III-VI₂ semiconductor thin film solar cells (Marrón et al., 2005; Minemoto et al., 2010; Romeo et al., 2006; Tiwari et al., 1999).

Here, we focus on advantages of the lift-off process in fabrication of flexible Cu(In,Ga)Se₂ (CIGS) thin film solar cells. For example, for the fabrication process where CIGS layers were directly grown on flexible substrates, Ti foils (Hartmann et al., 2000; Herz et al., 2003; Ishizuka et al., 2009a; Kapur et al., 2002; Kessler et al., 2005; Yagioka & Nakada, 2009), Cu steel sheets (Herz et al., 2003), Mo foils (Kapur et al., 2002, 2003), stainless steel sheets (Britt et al., 2008; Gedhill et al., 2011; Hashimoto et al., 2003; Kessler et al., 2005; Khelifi et al., 2010; Pinarbasi et al., 2010; Satoh et al., 2000, 2003; Shi et al., 2009; Wuerz et al., 2009), Al foils (Brémaud et al., 2007), Fe/Ni alloy foils (Hartmann et al., 2000), ZrO₂ sheets (Ishizuka et al., 2008a, 2008b, 2009b, 2010), and polyimide (PI) films (Brémaud et al., 2005; Caballero et al., 2009; Hartmann et al., 2000; Ishizuka et al., 2008c; Kapur et al., 2003; Kessler et al., 2005; Rudmann et al., 2005; Zachmann et al., 2009;), are used as flexible substrates. Since these materials do not include Na, other processes to introduce Na are required (Caballero et al., 2009; Ishizuka et al., 2008a; Keyes et al., 1997). Since the thermal tolerance temperature of a PI film is ~450°C, the low temperature growth of a CIGS layer is required. The first of the advantages of the lift-off process is to enable to use a high quality CIGS layer grown on a conventional Mo/soda-lime glass (SLG) substrate in the flexible solar cell fabrication. Consequently, the low temperature growth technology for high quality CIGS layer formation and novel processes for a Na source are not required. The second is to enable to use low thermal tolerance films as the flexible substrate of a CIGS solar cell, because in the CIGS solar cell fabrication process, the highest temperature process is the growth of a CIGS layer and the process temperature after the growth of a CIGS layer is less than 100°C.

2. Experimental

2.1 Flexible Cu(In,Ga)Se₂ solar cell fabrication procedure

A schematic illustration of the fabrication procedure of our flexible CIGS solar cell using the lift-off process is shown in Fig. 1 (Minemoto et al., 2010). A 0.8-μm-thick Mo layer was deposited on an SLG substrate without intentional substrate heating by the radio frequency (RF) magnetron sputtering method. A 2.5-μm-thick CIGS layer was deposited on the Mo/SLG substrate by the three-stage deposition process at the highest substrate temperature of approximately 550°C (Contreras et al., 1994a; Negami et al., 2002). From energy dispersive x-ray spectrometry measurements, the Cu, In, Ga, and Se composition ratios of this CIGS layer were approximately 23, 18, 8, and 51%, respectively. The

[Cu]/[Ga+In] and [Ga]/[Ga+In] ratios of the CIGS layer were therefore calculated to be ~0.88 and ~0.31, respectively. After CIGS surface cleaning by a KCN solution, a 0.2- μm -thick Au layer was deposited on the CIGS surface by a resistive evaporation method as a back electrode. The samples were annealed for 30 min at 250°C in N₂ ambient. Flexible films were bonded onto support SLG substrates with a silicone adhesion bond for preparation of the alternative substrates. These alternative substrates were also bonded onto the Au/CIGS/Mo/SLG structure with conductive epoxy glue. To dry the conductive epoxy glue, the samples were annealed on a hot plate at 100°C for 10 min in the atmosphere. Then, the alternative-sub./epoxy/Au/CIGS stacked structures were detached from the primary Mo/SLG substrates by applying tensile strain. In this detachment, the CIGS layer was transferred to the alternative substrate side (Marrón et al., 2005). The lift-off flexible CIGS solar cells were fabricated using this peeled CIGS layer. After cleaning of the CIGS rear surface by a KCN solution, a 0.1- μm -thick CdS layer was deposited on the CIGS rear surface by the chemical bath deposition method. 0.1- μm -thick i-ZnO and 0.1- μm -thick In₂O₃:Sn layers were deposited by the RF magnetron sputtering method. Al/NiCr grids were formed. Finally, the flexible CIGS solar cells using the lift-off process were completed by detaching the flexible films from the support SLG substrates. For comparison, we also prepared a standard solar cell where the lift-off process was not carried out (the Al/NiCr/In₂O₃:Sn/ZnO/CdS/CIGS/Mo/SLG structure). The properties of the films used in this study are summarized in Table 1. Figure 2 shows a photograph of the flexible solar cells using the PI film.

Material	PI	PTFE	Polyester
Thermal tolerance temperature (°C)	450	260	120
Thickness (μm)	55	120	25

Table 1. Properties of PI, polytetrafluoroethylene (PTFE) and polyester films used in this study are summarized.

2.2 Characterization methods

Current density-voltage (*J-V*) measurements were performed under standard air mass 1.5 global conditions (100 mW/cm²) at 25°C. External quantum efficiency (EQE) measurements of the AC mode were performed at 25°C under white light bias (~0.3 sun) conditions. The laser-beam-induced current (LBIC) method using the laser diode (λ : 783 nm, laser power: 0.3 mW) was performed to investigate a spatial distribution of an EQE (Minemoto et al., 2005). In LBIC measurements, a nominal spot size is less than 50 μm and a scan step is 53 μm . The surfaces of the fabricated flexible solar cells were observed with an optical microscope. The *J-V*, EQE, and LBIC measurements were performed after light soaking.

3. Results and discussion

3.1 Characterization of flexible Cu(In,Ga)Se₂ solar cells fabricated using lift-off process

The *J-V* characteristics of the fabricated flexible solar cells are shown in Fig. 3. For comparison, the *J-V* characteristic of the standard solar cell is also shown. Solar cell parameters such as the short-circuit current density (*J*_{sc}), the open-circuit voltage (*V*_{oc}), the




Fig. 1. Schematic illustration of fabrication procedure of flexible CIGS solar cell using lift-off process.




Fig. 2. Photograph of flexible CIGS solar cells using PI film.




Fig. 3. Photo *J-V* curves of flexible solar cells using PTFE (red) and PI (blue) films. Photo *J-V* curve of standard solar cell without lift-off process (brack) is also shown for comparison.

Sample structure	<i>Eff.</i> (%)	<i>J_{sc}</i> (mA/cm ²)	<i>V_{oc}</i> (V)	<i>FF</i> (%)
PI flexible	5.9	25.7	0.420	54.9
PTFE flexible	6.6	25.6	0.445	57.9
Standard	11.4	36.9	0.497	62.4

Table 2. Solar cell parameters obtained from flexible solar cells using PI and PTFE films. Solar cell parameters of standard solar cell are also shown for comparison.

conversion efficiency ($Eff.$), and the fill factor (FF) are summarized in Table 2. The conversion efficiencies of the flexible solar cells are an approximately half conversion efficiency of the standard solar cell. EQE spectra of these solar cells are shown in Fig. 4. EQEs of the flexible solar cells remarkably decrease in the long wavelength region from 700 to 1200 nm compared to the standard solar cell. We discuss this cause as below.




Fig. 4. EQE spectra of flexible solar cells using PTFE (red) and PI films (blue). EQE spectrum of standard solar cell without lift-off process (black) is also shown for comparison. EQE spectra of flexible solar cells are similar irrespective of substrate materials.

As shown in Fig. 5(a), the band gap profile of the standard solar cell consists of the graded band gap structure because of the three-stage deposition process. The diffusion length of electrons generated by the long wavelength light near the back electrode is improved due to the quasi-electric field in which the CIGS layer forms (Contreras et al., 1994b). The graded band gap structure is therefore beneficial for collecting the photogenerated carriers. On the other hand, as shown in Fig. 5(b), the band gap profile of the CIGS layer is inverted due to




Fig. 5. Schematic illustrations of band gap profiles of CIGS layers. CIGS absorber layers with (a) double graded band gap and (b) inverted double graded band gap structures are shown.

the lift-off process for the flexible solar cells. We speculate that the band gap profile of the inverted graded band gap structure is not beneficial for collecting the photogenerated carriers by long wavelength light. We conclude that the EQE reductions observed for the flexible solar cells are attributed to the influence of the inverted graded band gap structure. We describe an interesting point of our flexible solar cells as below. Different materials with different thermal tolerance temperatures are used as the flexible substrates of these flexible solar cells, as shown in Table 1. These flexible solar cells, however, show the similar characteristics irrespective of the flexible film materials from Fig. 3 and Fig. 4. LBIC and optical microscope images of the flexible solar cell using the PTFE film are shown in Figs. 6(a) and 6(b), respectively. There is a low EQE region on the lower side of the solar cell from Fig. 6(a). This low EQE region corresponds approximately to the flexurelike region from a comparison between Figs. 6(a) and 6(b). This result therefore suggests that this flexure cause reduction of an EQE. LBIC and optical microscope images of the standard solar cell are shown in Figs. 6(c) and 6(d), respectively. In contrast, the LBIC and optical microscope images are uniform for the standard solar cell.




Fig. 6. (a) LBIC and (b) optical microscope images of flexible solar cell using PI film. (c) LBIC and (d) optical microscope images of standard solar cell. Indicators of EQE intensity are shown next to LBIC images.




Fig. 7. Schematic illustration of fabrication procedure of flexible CIGS solar cell using (Zn_{0.83}Mg_{0.17})O window layer and lift-off process.

3.2 Development of Cd-free flexible Cu(In,Ga)Se₂ solar cells

We developed a new Cd-free flexible CIGS solar cell using a (Zn,Mg)O window layer. The fabrication procedure is shown in Fig. 7. This process is basically similar to Fig. 1. We deposited a 0.1- μm -thick (Zn_{0.83}Mg_{0.17})O window layer in stead of the ZnO window/CdS buffer layers. The RF magnetron cosputtering method using ZnO and MgO targets was used as the deposition technique (Minemoto et al., 2000, 2001). We also deposited a 0.2- μm -thick Ni layer by the resistive evaporation method as the back electrode in stead of the Au layer. In this subsection, a 55- μm -thick polyester film was used as a flexible substrate. Interestingly, when the flexible solar cell using the polyester film was separated from the support SLG substrate, the detachment occurred not at the support SLG/polyester interface but at the polyester/epoxy interface due to the weaker adhesion at the polyester/epoxy interface. After the substrate-free structure was once, the polyester film was therefore bonded onto the rear surface of the solar cell with a silicone adhesion bond. The photograph of the flexible solar cells fabricated via the above procedure is shown in Fig. 8. We also prepared not only the flexible solar cells using the conventional ZnO window/CdS buffer layers but also the solar cells without the lift-off process for comparison.




Fig. 8. Photograph of flexible solar cells using polyester film. Left solar cells are Cd-free solar cells using (Zn,Mg)O window layer. Right solar cells consist of conventional ZnO window/CdS buffer layers structure.

The *J-V* characteristics of the flexible solar cells are shown in Fig. 9. The results of the standard solar cells without the lift-off process are also shown in Fig. 9. Solar cell parameters obtained from the *J-V* characteristics are summarized in Table 3. All parameters of the ZnO/CdS solar cell is higher than those of the (Zn,Mg)O solar cell for the standard solar cells. On the other hand, although there are the differences in the window layer/ buffer layer structures for the flexible solar cells, these flexible solar cells show the similar properties.




Fig. 9. Photo *J-V* curves of flexible solar cells using (Zn,Mg)O window layer and conventional ZnO window/CdS buffer layers. Photo *J-V* curves of standard solar cells without lift-off process are also shown for comparison.

EQE spectra of these solar cells are shown in Fig. 9. EQEs of the (Zn,Mg)O standard solar cell are higher than those of the ZnO/CdS standard solar cell in the region from 300 to 480 nm, because the band gap of (Zn_{0.83}Mg_{0.17})O is higher than those of CdS and ZnO (Minemoto et al., 2000). These high EQEs in this region is therefore attributed to a low transmission loss of the short wavelength light. Moreover, the tendency of this result is also observed for the flexible solar cells. We found that the (Zn,Mg)O window layer structure was effective for reducing a transmission loss of the short wavelength light even in our flexible solar cells.

Sample structure	Eff. (%)	<i>J</i> _{sc} (mA/cm ²)	<i>V</i> _{oc} (V)	FF (%)
(Zn,Mg)O flexible	1.0	14.8	0.231	30.5
ZnO/CdS flexible	1.0	14.8	0.227	30.2
(Zn,Mg)O standard	8.3	32.4	0.465	54.9
ZnO/CdS standard	13.7	34.9	0.562	70.0

Table 3. Summary of solar cell parameters obtained from flexible solar cells using (Zn,Mg)O window layer and conventinal ZnO window/CdS buffer layers. For comparison, solar cell parametaers obtained from standard solar cells using (Zn,Mg)O window layer and ZnO window/CdS buffer layers are also summarized.




Fig. 10. EQE spectra of flexible solar cells using (Zn,Mg)O window layer (red) and conventional ZnO window/CdS buffer layers (blue). EQE spectra of standard solar cells using (Zn,Mg)O window layer (dark red) and ZnO window/CdS buffer layers (dark blue) are also shown for comparison.

Here, we discuss why these flexible solar cells showed the similar solar cell parameters. In this subsection, we used Ni instead of Au as a back electrode material. In subsection 3.1, the ZnO/CdS flexible solar cells with the Au back electrode showed a conversion efficiency of ~6%. We think that the Ni back electrode may limit performance of these solar cells. We therefore speculate that the Ni atoms, which diffused into the CIGS layer from the back side due to the low temperature annealing, behave as recombination centers for electrons.

4. Conclusion

After we described the review of the lift-off process, we also described the advantages of the lift-off process in the flexible CIGS solar cell fabrication. We developed the fabrication procedure of the flexible CIGS solar cells using the lift-off process. The characteristics of the flexible solar cells were shown compared to the standard solar cell. Although the conversion efficiencies of the flexible solar cells using the lift-off process are an approximately half conversion efficiency of the standard solar cell, the flexible solar cells showed the similar characteristics irrespective of the substrate materials. Moreover, we attempted the concept of a Cd-free solar cell. We found that the choice of back electrode materials is a crucial problem rather than the window layer/buffer layer structure. We expect that the lift-off process further advances through our results.

5. Acknowledgment

This work was partially supported by the Ministry of Education, Culture, Sports, Science and Technology (MEXT) through a Grant-in-Aid for Young Scientists (B). The authors are

grateful to Dr. T. Negami of Pnasonic Electric Works Co., Ltd., for useful discussion. The authors would like to thank Mr. T. Yagi and Associate Professor S. Ikeda of Osaka University for their technical support in EQE measurements.

6. References

- Kamath, G. S.; Ewan, J. & Knechtli R. C. (1977). Large-Area High-Efficiency (AlGa)As-GaAs Solar Cells. *IEEE Transactions on Electron Devices*, Vol. ED-24, No. 4, (April 1977), pp. 473-475, ISSN 0018-9383
- Woodall, J. M. & Hovel, H. J. (1977). An isothermal etchback-regrowth method for high efficiency $\text{Ga}_{1-x}\text{Al}_x\text{As}$ -GaAs solar cells. *Applied Physics Letters*, Vol. 30, No. 9, (February 1977), pp. 492-494, ISSN 0003-6951
- Konagai, M.; Sugimoto, M. & Takahashi, K. (1978). HIGH EFFICIENCY GaAs THIN FILM SOLAR CELLS BY PEELED FILM TECHNOLOGY. *Journal of Crystal Growth*, Vol. 45, (December 1978), pp. 277-280, ISSN 0022-0248
- Geelen, A. V.; Hageman, P. R. Bauhuis, G. J. Rijsingen, P. C. V. Schmidt, P. & Giling, L. J. (1997). Epitaxial lift-off GaAs solar cell from a reusable GaAs substrate. *Material Science and Engineering B*, Vol. 45, (March 1997), pp. 162-171, ISSN 0921-5107
- Schermer, J. J.; Bauhuis, G. J. Mulder, P. Meulemeesters, W. J. Haverkamp, E. Voncken, M. M. A. J. & Larsen, P. K. (2000). High rate epitaxial lift-off on InGaP films from GaAs substrate. *Applied Physics Letters*, Vol. 76, No. 15, (April 2000), pp. 2131-2133, ISSN 0003-6951
- Schermer, J. J.; Mulder, P. Bauhuis, G. J. Voncken, M. M. A. J. Deelen, J. V. Haverkamp, E. & Larsen, P. K. (2005a). Epitaxial Lift-Off for large area thin film III/V devices. *Physica Status Solidi A*, Vol. 202, (February 2005), pp. 501-508, ISSN 1862-6300
- Voncken, M. M. A. J.; Schermer, J. J. Maduro, G. Bauhuis, G. J. Mulder, P. & Larsen, P. K. (2002). Influence of radius of curvature on the lateral etch rate of the weight induced epitaxial lift-off process. *Materials Science and Engineering B*, Vol. 95, (September 2002) pp. 242-248, ISSN 0921-5107
- Yablonovitch, E.; Gmitter, T. Harbison, J. P. & Bhant, R. (1987). Extreme selectivity in the lift-off epitaxial GaAs films. *Applied Physics Letters*, (December 1987), pp. 2222-2224, ISSN 0003-6951
- McClelland, R. W.; Bozler, C. O. & Fan, J. C. C. (1980). A technique for producing epitaxial films on reusable substrate. *Applied Physics Letters*, Vol. 37, No. 6, (September 1980), pp. 560-562, ISSN 0003-6951
- Schermer, J. J.; Bauhuis, G. J. Mulder, P. Haverkamp, E. J. Deelen, J. V. Niftrik, A. T. J. V. & Larsen, P. K. (2006). Photon confinement in high-efficiency thin-film III-V solar cells obtained by epitaxial lift-off. *Thin Solid Films*, Vol. 511-512, (January 2006), pp. 645-653, ISSN 0040-6090
- Bauhuis, G. J.; Mulder, P. Haverkamp, E. J. Huijben, J. C. C. M. & Schermer, J. J. 26.1% thin-film GaAs solar cell using epitaxial lift-off. *Solar Energy Materials and Solar Cells*, Vol. 93, (May 2009), pp. 1488-1491, ISSN 0927-0248
- Schermer, J. J.; Mulder, P. Bauhuis, G. J. Larsen, P. K. Oomen G. & Bongers E. (2005b) Thin-film GaAs Epitaxial Lift-off Solar Cells for Space Applications. *Progress in Photovoltaics: Research and Applications*, Vol. 13, (April 2005), pp. 587-596, ISSN 1062-7995

- Bergmann, R. B.; Berge, C. Rinke, T. J. Schmidt, J. & Werner, J. H. (2002). Advances in monocrystalline Si thin film solar cells by layer transfer. *Solar Energy Materials and Solar Cells*, Vol. 74, (October 2002), pp. 213-218, ISSN 0927-0248
- Brendel, R. (2001). Review of Layer Transfer Processes for Crystalline Thin-Film Silicon Solar Cells. *Japanese Journal of Applied Physics*, Vol. 40, No. 7, (July 2001), pp. 4431-4439, ISSN 0021-4922
- Marrón, D. F.; Meeder, A. Sadewasser, S. Würz, R. Kaufmann, C. A. Glatzel, T. Schedel-Niedrig, T. & Lux-Steiner, M. C. Lift-off process and rear-side characterization of CuGaSe₂ chalcopyrite thin films and solar cells. *Journal of Applied Physics*, Vol. 97, (April 2005), pp. 094915-1-094915-7, ISSN 0021-8979
- Minemoto, T.; Abe, Y. Anegawa, T. Osada, S. & Takakura, H. (2010). Lift-Off Process for Flexible Cu(In,Ga)Se₂ Solar Cells. *Japanese Journal of Applied Physics*, Vol. 49, No. 4, (April 2010), pp. 04DP06-1-04DP06-3, ISSN 0021-4922
- Romeo, A.; Khrypunov, G. Kurdesau, F. Arnold, M. Bätzner, D. L. Zogg, H. & Tiwari, A. N. High-efficiency flexible CdTe solar cells on polymer substrates. *Solar Energy Materials and Solar Cells*, Vol. 90, (November 2006), pp. 3407-3415, ISSN 0927-0248
- Tiwari, A. N.; Krejci, M. Haung, F.-J. & Zogg, H. (1999). 12.8% Efficiency Cu(In,Ga)Se₂ Solar Cell on a Flexible Polymer Sheet. *Progress in Photovoltaics: Research and Applications*, Vol. 7, (October 1999), pp. 393-397, ISSN 1062-7995
- Hartmann, M.; Schmidt, M. Jasenek, A. Schock, H. W. Kessler, F. Herz, K. & Powalla, M. Flexible and light weight substrates for Cu(In,Ga)Se₂ solar cells and modules, *Conference Record of the Twenty-Eighth IEEE Photovoltaic Specialists Conference 2000*, pp. 638-641, ISBN 0-7803-5772-8, Anchorage, Alaska, USA, September 15-22, 2000
- Herz, K.; Eicke, A. Kessler, F. Wächter, R. & Powalla, M. (2003). Diffusion barriers for CIGS solar cells on metallic substrates. *Thin Solid Films*, Vol. 431-432, (May 2003), pp. 392-397, ISSN 0040-6090
- Ishizuka, S.; Yamada, A. & Niki, S. (2009a). Efficiency enhancement of flexible CIGS solar cells using alkali-silicate glass thin layers as an alkali source material, *Conference Record of the Thirty-Forth IEEE Photovoltaic Specialists Conference 2009*, pp. 002349-002353, ISBN 978-1-4244-2949-3, Philadelphia, Pennsylvania, USA, June 7-12, 2009
- Kapur, V. K.; Bansal, A. Phucan L. & Asensio, O. I. (2002). Non-vacuum printing process for CIGS solar cells on rigid and flexible substrates, *Conference Record of the Twenty-Ninth IEEE Photovoltaic Specialists Conference 2002*, pp. 688-691, ISBN 0-7803-7471-1, New Orleans, Louisiana, USA, May 19-24, 2002
- Kessler, F.; Herrmann, D. & Powalla, M. (2005). Approaches to flexible CIGS thin-film solar cells. *Thin Solid Films*, Vol. 480-481, (December 2005), pp. 491-498, ISSN 0040-6090
- Yagioka, T. & Nakada, T. (2009). Cd-Free Flexible Cu(In,Ga)Se₂ Thin Film Solar Cells with ZnS(O,H) Buffer Layers on Ti Foils. *Applied Physics Express*, Vol. 2, No. 7, (June 2009), pp. 072201-1-072201-3, ISSN 1882-0778
- Kapur, V. K.; Bansal, A. Le, P. & Asensio, O. I. (2003). Non-vacuum processing of CuIn_{1-x}Ga_xSe₂ solar cells on rigid and flexible substrates using nanoparticle precursor inks. *Thin Solid Films*, Vol. 431-432, (May 2003), pp 53-57, ISSN 0040-6090
- Britt, J. S.; Wiedeman, S. Schoop, U. & Verebelyi, D. (2008). High-volume manufacturing of flexible and lightweight CIGS solar cells, *Conference Record of the Thirty-Third IEEE*


- Photovoltaic Specialists Conference 2008*, pp. 574-577, ISBN 978-1-4244-2949-3, San Diego, California, USA, May 11-16, 2008
- Gledhill, S.; Zykov, A. Allsop, N. Rissom, T. Schniebs, J. Kaufmann, C. A. Lux-Steiner, M. & Fischer, Ch-H. (2011). Spray pyrolysis of barrier layers for flexible thin film solar cells on steel. *Solar Energy Material and Solar Cells*, Vol. 95, (February 2011) pp. 504-509, ISSN 0927-0248
- Hashimoto, Y.; Satoh, T. Shimakawa, S. & Negami, T. (2003). High efficiency CIGS solar cell on flexible stainless steel, *Proceedings of third World Conference on Photovoltaic Energy Conversion 2003*, pp. 574-577, ISBN 4-9901816-0-3, Osaka, Japan, May 11-18, 2003
- Khelifi, S.; Belghachi, A. Lauwaert, J. Decock, K. Wienke, J. Caballero, R. Kaufmann, C. A. & Burgelman, M. (2010). Characterization of flexible thin film CIGSe solar cells grown on different metallic foil substrates. *Energy Procedia*, Vol. 2, (August 2010), pp. 109-117, ISSN 1876-6102
- Pinarbasi, M.; Aksu, S. Freitag, J. Boone, T. Zolla, H. Vasquez, J. Nayak, D. Lee, E. Wang, T. Abushama, J. & Metin, B. (2001). FLEXIBLE CELLS AND MODULES PRODUCED USING ROLL-TO-ROLL ELECTROPLATING APPROACH, *Conference Record of the Thirty-Fifth IEEE Photovoltaic Specialists Conference 2010*, pp. 000169-000174, ISBN 978-1-4244-5890-5, Honolulu, Hawaii, USA, June 20-25, 2010
- Satoh, T.; Hashimoto, Y. Shimakawa, S. Hayashi, S. & Negami, T. (2000). CIGS solar cells on flexible stainless steel substrates, *Conference Record of the Twenty-Eighth IEEE Photovoltaic Specialists Conference 2000*, pp. 567-570, ISBN 0-7803-5772-8, Anchorage, Alaska, USA, September 15-22, 2000
- Satoh, T.; Hashimoto, Y. Shimakawa, S. Hayashi, S. & Negami, T. (2003). Cu(In,Ga)Se₂ solar cells on stainless steel substrates covered with insulating layers. *Solar Energy Materials and Solar Cells*, Vol. 75, (January 2003), pp. 65-71, ISSN 0927-0248
- Shi, C. Y.; Sun, Y. He, Q. Li, F. Y. & Zhao, J. C. (2009). Cu(In,Ga)Se₂ solar cells on stainless-steel substrates covered with ZnO diffusion barriers. *Solar Energy Materials and Solar Cells*, Vol. 93, (May 2009), pp. 654-656, ISSN 0927-0248
- Wuerz, R.; Eicke, A. Frankenfeld, M. Kessler, F. Powalla, M. Rogin, P. & Yazdani-Assl, O. (2009). CIGS thin-film solar cells on steel substrates. *Thin Solid Films*, Vol. 517, (February 2009), pp. 2415-2418, ISSN 0040-6090
- Brémaud, D.; Rudmann, D. Kaelin, M. Ernits, K. Bilger, G. Döbeli, M. Zogg, H. & Tiwari, A. N. (2007). Flexible Cu(In,Ga)Se₂ on Al foils and the effects of Al during chemical bath deposition. *Thin Solid Films*, Vol. 515, (May 2007), pp. 5857-5861, ISSN 0040-6090
- Ishizuka, S.; Yamada, A. Matsubara, K. Fons, P. Sakurai, K. & Niki, S. (2008a). Alkali incorporation control in Cu(In,Ga)Se₂ thin films using silicate thin layers and applications in enhancing flexible solar cell efficiency. *Applied Physics Letters*, Vol. 93, (September 2008), pp. 124105-1-124105-3, ISSN 0003-6951
- Ishizuka, S.; Yamada, A. Fons, P. & Niki, S. (2008b). Flexible Cu(In,Ga)Se₂ solar cells fabricated using alkali-silicate glass thin layers as an alkali source material. *Journal of Renewable and Sustainable Energy*, Vol. 1, (November 2008), pp. 013102-1-013102-8, ISSN 1941-7012
- Ishizuka, S.; Yamada, A. Matsubara, K. Fons, P. Sakurai, K. & Niki, S. (2009b). Development of high-efficiency flexible Cu(In,Ga)Se₂ solar cells: A study of alkali doping effects

- on CIS, CIGS, and CGS using alkali-silicate glass thin layers. *Current Applied Physics*, Vol. 10, (November 2009), pp. S154-S156, ISSN 1567-1739
- Ishizuka, S.; Yoshiyama, T. Mizukoshi, K. Yamada, A. & Niki, S. (2010). Monolithically integrated flexible Cu(In,Ga)Se₂ solar cell submodules. *Solar Energy Materials and Solar Cells*, Vol. 94, (July 2010), pp. 2052-2056, ISSN 0927-0248
- Kapur, V. K.; Bansal, A. Le, P. Asensio, O. & Shigeoka, N. (2003). Non-vacuum processing of CIGS solar cells on flexible polymeric substrates, *Proceedings of third World Conference on Photovoltaic Energy Conversion 2003*, pp. 465-468, ISBN 4-9901816-0-3, Osaka, Japan, May 11-18, 2003
- Brémaud, D.; Rudmann, D. Bilger, G. Zogg, H. & Tiwari, A. N. (2005). Towards the development of flexible CIGS solar cells on polymer films with efficiency exceeding 15%, *Conference Record of the Thirty-first IEEE Photovoltaic Specialists Conference 2005*, pp. 223-226, ISBN 0-7803-8707-4, Orlando, Florida, USA, January 3-7, 2005
- Caballero, R.; Kaufmann, C. A. Eisenbarth, T. Unold, T. Schorr, S. Hesse, R. Klenk, R. & Schock, H.-W. (2009). The effect of NaF precursors on low temperature growth of CIGS thin film solar cells on polyimide substrates. *Physica Status Solidi A*, Vol. 206, (May 2009), pp. 1049-1053, ISSN 1862-6300
- Ishizuka, S.; Hommoto, H. Kido, N. Hashimoto, K. Yamada, A. & Niki, S. (2008c). Efficiency Enhancement of Cu(In,Ga)Se₂ Solar Cells Fabricated on Flexible Polyimide Substrates using Alkali-Silicate Glass Thin Layers. *Applied Physics Express*, Vol. 1, No. 9, (September 2008), pp. 092303-1-092303-3, ISSN 1882-0778
- Rudmann, D.; Brémaud, D. Zogg, H. & Tiwari, A. N. (2005). Na incorporation into Cu(In,Ga)Se₂ for high-efficiency flexible solar cells on polymer foils. *Journal of Applied Physics*, Vol. 97, (August 2005), pp. 084903-1-084903-5, ISSN 0021-8979
- Zachmann, H.; Heinker, S. Braun, A. Mudryi, A. V. Gremenok, V. F. Ivaniukovich, A. V. & Yakushev, M. V. (2009). Characterisation of Cu(In,Ga)Se₂-based thin film solar cells on polyimide. *Thin Solid Films*, Vol. 517, (February 2009), pp. 2209-2212, ISSN 0040-6090
- Keyes, B. M.; Hasoon, F. Dipppo, P. Balcioglu, A. & Abulfotuh, F. (1997). INFLUENCE OF Na ON THE ELECTRO-OPTICAL PROPERTIES OF Cu(In,Ga)Se₂, *Conference Record of the Twenty-Sixth IEEE Photovoltaic Specialists Conference*, pp. 479-482, ISBN 0-7803-3767-0, Anaheim, California, USA, September 29-October 3, 1997
- Contreras, M. A.; Gabor, A. M. Tennant, A. Asher, S. Tuttle, J. & Noufi, R. (1994a). Accelerated publication 16.4% total-area conversion efficiency thin-film polycrystalline MgF₂/ZnO/CdS/Cu(In,Ga)Se₂/Mo solar cell. *Progress in Photovoltaics: Research and Applications*, Vol. 2, (October 1994) pp. 287-292, ISSN 1062-7995
- Negami, T.; Satoh, T. Hashimoto, Y. Shimakawa, S. Hayashi, S. Muro, M. Inoue, H. & Kitagawa, M. (2002). Production technology for CIGS thin film solar cells. *Thin Solid Films*, Vol. 403-404, (January 2002), pp. 197-203, ISSN 0040-6090
- Minemoto, T.; Okamoto, C. Omae, S. Murozono, M. Takakura, H. Hamakawa, Y. (2005). Fabrication of Spherical Silicon Solar Cells with Semi-Light-Concentration System. *Japanese Journal of Applied Physics*, Vol. 44, No. 7A, (July 2005), pp. 4820-4824, ISSN 0021-4922
- Contreras, M. A.; Tuttle, J. Gabor, A. Tennant, A. Ramanathan, K. Asher, S. Franz, A. Keane, J. Wang, L. Scofield, J. & Noufi, R. (1994b). HIGH EFFICIENCY Cu(In,Ga)Se₂-

BASED SOLAR CELLS: PROCESSING OF NOVEL ABSORBER STRUCTURES, *Proceedings of the First World Conference on Photovoltaic Energy Conversion 1994*, pp. 68-75, ISBN 0-7803-1460-3, Waikoloa, Hawaii, USA, December 5-9, 1994

Minemoto, T.; Negami, T. Nishiwaki, S. Takakura, H. & Hamawaka, Y. (2000). Preparation of $\text{Zn}_{1-x}\text{Mg}_x\text{O}$ films by radio frequency magnetron sputtering. *Thin Solid Films*, Vol. 372, (August 2000), pp. 173-176, ISSN 0003-6951

Minemoto, T.; Hashimoto, Y. Satoh, T. Negami, T. Takakura, H. & Hamakawa, Y. (2001). $\text{Cu}(\text{In,Ga})\text{Se}_2$ solar cells with controlled conduction band offset of window/ $\text{Cu}(\text{In,Ga})\text{Se}_2$ layers. *Journal of Applied Physics*, Vol. 89, (June 2001), pp. 8327-8330, ISSN 0021-8979



Solar Cells - Thin-Film Technologies

Edited by Prof. Leonid A. Kosyachenko

ISBN 978-953-307-570-9

Hard cover, 456 pages

Publisher InTech

Published online 02, November, 2011

Published in print edition November, 2011

The first book of this four-volume edition is dedicated to one of the most promising areas of photovoltaics, which has already reached a large-scale production of the second-generation thin-film solar modules and has resulted in building the powerful solar plants in several countries around the world. Thin-film technologies using direct-gap semiconductors such as CIGS and CdTe offer the lowest manufacturing costs and are becoming more prevalent in the industry allowing to improve manufacturability of the production at significantly larger scales than for wafer or ribbon Si modules. It is only a matter of time before thin films like CIGS and CdTe will replace wafer-based silicon solar cells as the dominant photovoltaic technology. Photoelectric efficiency of thin-film solar modules is still far from the theoretical limit. The scientific and technological problems of increasing this key parameter of the solar cell are discussed in several chapters of this volume.

How to reference

In order to correctly reference this scholarly work, feel free to copy and paste the following:

Yasuhiro Abe, Takashi Minemoto and Hideyuki Takakura (2011). Development of Flexible Cu(In,Ga)Se₂ Thin Film Solar Cell by Lift-Off Process, Solar Cells - Thin-Film Technologies, Prof. Leonid A. Kosyachenko (Ed.), ISBN: 978-953-307-570-9, InTech, Available from: <http://www.intechopen.com/books/solar-cells-thin-film-technologies/development-of-flexible-cu-in-ga-se2-thin-film-solar-cell-by-lift-off-process>

INTECH
open science | open minds

InTech Europe

University Campus STeP Ri
Slavka Krautzeka 83/A
51000 Rijeka, Croatia
Phone: +385 (51) 770 447
Fax: +385 (51) 686 166
www.intechopen.com

InTech China

Unit 405, Office Block, Hotel Equatorial Shanghai
No.65, Yan An Road (West), Shanghai, 200040, China
中国上海市延安西路65号上海国际贵都大饭店办公楼405单元
Phone: +86-21-62489820
Fax: +86-21-62489821

© 2011 The Author(s). Licensee IntechOpen. This is an open access article distributed under the terms of the [Creative Commons Attribution 3.0 License](https://creativecommons.org/licenses/by/3.0/), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

IntechOpen

IntechOpen